



## Pebax Heat Shrink Tubing

Cobalt Polymers offer the world's best Pebax Heat Shrink Tubing.

- Exceptional compression and strength
- Bonds to regular Pebax Tubing
- Expansion ratios of 2:1 and 4:1
- Full range of Durometers and Colors available
- Thinnest Pebax tubing available anywhere
- Standard sizes for requirements between 0.007" (0.17 mm) and 0.250" (6.3 mm)

Palladium Heat Shrink offers industry leading properties of comprehensive strength, toughness, wall thickness, and flexibility. Its surface flow property provides excellent grip onto polymer or metal substrates.

### Available Stock Sizes:

#### 72 Durometer

#### '2:1' Shrink PALLADIUM™ Tubing

Expanded (min)	ID Recovered ID (max)	Wall Thickness (recovered)	Color	Product ID
0.014" (0.3mm)	0.007" (0.1mm)	0.002" (.05mm)	Clear	P2-014-002-CLR
0.036" (0.9mm)	0.020" (0.5mm)	0.004" (0.1mm)	Clear	P2-040-004-CLR
0.036" (0.9mm)	0.020" (0.5mm)	0.004" (0.1mm)	Black	P2-040-004-BLK
0.060" (1.5mm)	0.035" (0.9mm)	0.010" (0.25mm)	Clear	P2-060-010-CLR
0.060" (1.5mm)	0.035" (0.9mm)	0.003" (.07mm)	Clear	P2-060-003-CLR
0.130" (3.3mm)	0.075" (1.9mm)	0.006" (0.15mm)	Clear	P2-140-006-CLR

#### 40 Durometer

#### '2:1' Shrink PALLADIUM™ Tubing

Expanded (min)	ID Recovered ID (max)	Wall Thickness (recovered)	Color	Product ID
0.036" (0.9mm)	0.020" (0.5mm)	0.004" (0.1mm)	Clear	P2-040-004-40-CLR
0.060" (1.5mm)	0.035" (0.9mm)	0.003" (.07mm)	Clear	P2-060-003-40-CLR
0.060" (1.5mm)	0.035" (0.9mm)	0.010" (0.25mm)	Clear	P2-060-010-40-CLR
0.130" (3.3mm)	0.075" (1.9mm)	0.006" (0.15mm)	Clear	P2-140-006-40-CLR

#### 72 Durometer

#### '4:1' Shrink PALLADIUM™ Tubing

Expanded (nominal)	ID Recovered ID (max)	Wall Thickness (supplied/recovered)	Color	Product ID
0.070" (1.7mm)	0.021" (0.5mm)	0.0006" / 0.004" (0.1mm)	Clear	P4-080-004-CLR
0.070" (1.7mm)	0.021" (0.5mm)	0.0006" / 0.004" (0.1mm)	Black	P4-080-004-BLK
0.098" (2.5mm)	0.035" (0.9mm)	0.0015" / 0.010" (0.25mm)	Clear	P4-120-010-CLR
0.120" (3.0mm)	0.035" (0.9mm)	0.0005" / 0.003" (.07mm)	Clear	P4-120-003-CLR
0.250" (6.3mm)	0.070" (1.7mm)	0.0008" / 0.006" (0.15mm)	Clear	P4-280-006-CLR

### Additional Products

We offer sizes, colors, durometers to fit your engineering requirements. Contact customer service at (800) 337-0901 or visit [www.cobaltpolymers.com](http://www.cobaltpolymers.com) to order, get samples or for technical information

*Elemental Solutions in Tubing™*

Fall 2015 | Cobalt Update

**(800) 337-0901**  
sales@cobaltpolymers.com  
www.cobaltpolymers.com

## Typical Properties at 72 Durometer

Shrink Temperature:	340° F/171°C
Durometer (Shore D):	72 (other durometers are available)
Elongation at Break:	300%
Tensile Strength at Break:	7,500 PSI
Dielectric Strength:	>500 volts / mil
Tubing Certifications:	USP Class VI
Sterilization:	Gamma, E-Beam, ETO stable Test for autoclave or repeat use

## Attributes

Highly Flexible	Superior Surface Finish
Radiation Sterilization	Conformal, Tight Fitting
Low Longitudinal Shrinkage	High Compressive Fitting
USP Class VI	Tough, Durable Stable

## Applications

PEBAX outer layer for catheter shaft	Bridge large transitions
Wire Insulation	Cover splices
Strain relief	Manufacturing Aid
Cover Coils and Braids	

## R&D Package

Any 6 pieces from stock for \$85.00  
Mix and match with our other tubing lines  
Contact customer service at (800) 337-0901 or visit [www.cobaltpolymers.com](http://www.cobaltpolymers.com)

## Manufacturing Capabilities

Custom Sizes, Wall Thickness, Color and Resins  
Precision Cut Lengths  
Scoring and Slit Tubing  
Custom Expansion of Customer-supplied Tubing  
Continuous Re-Sizing (“necking”) of Thermoplastic Tubing

Cobalt Polymers manufactures precision polymer tubing for medical device and high technology applications with core strengths in Polymer Chemistry, Radiation Science and process Engineering.

## Elemental Solutions in Tubing



P.O. Box 579  
Cloverdale, CA 95425  
**(800) 337-0901 FAX: (707) 894-9083**  
[sales@cobaltpolymers.com](mailto:sales@cobaltpolymers.com)  
[www.cobaltpolymers.com](http://www.cobaltpolymers.com)

[www.cobaltpolymers.com](http://www.cobaltpolymers.com)  
**(800) 337-0901**

No warranty of fitness or suitability for a particular application or end-use product is expressed or implied.  
All values supplied here are for evaluation only and are typical. PEBAX is a trademark of Atofina.

Fall 2015 | Cobalt Update